


4 wherein  $R_3$  is an organic group selected from the group consisting of polyvalent  
 5 aliphatic or alicyclic and aromatic hydrocarbon,  $z$  is an integer of 1 to 3, and  
 6 B is S; and



7  
 8 wherein  $R_4$  is a substituted or unsubstituted aliphatic polyhydric alcohol residue,  
 9  $u$  is an integer of 1 or 2, and  $v$  is an integer of 2 to 4.

1 123. (Amended) The composition of claim 116 wherein the polyene is triallyl-  
 2 1,3, 5-triazine-2,4,6(1H, 3H, 5H)-trione.

1 129. (Amended) The process of claim 124 wherein the composition is cured by  
 2 heating the composition to a first temperature of about 0° to 60°C, then heating  
 3 the composition gradually to a second temperature of about 100 to 150°C over a  
 4 period of about 1 to 32 hours, maintaining the composition at the second  
 5 temperature for about 4 to 32 hours, then cooling the composition to a third  
 6 temperature of about 20 to 40°C over a period of about 1 to 32 hours.

1 134. (Amended) A curable monomer composition for making a linear  
 2 homogeneous terpolymer which terpolymer has a single glass transition  
 3 temperature, does not have any phase separation and which is optically clear

64

3

- 4 consisting essentially of the composition of claim 116 in solution in a solvent and
  - 5 which solution is polymerized or bulk polymerized at an elevated temperature to
  - 6 form the terpolymer.
- 
-